

AMENDMENT NO. 1 OCTOBER 2018
TO
IS 17049 : 2018 PETROLEUM COKE FOR ANODE
MAKING IN ALUMINIUM INDUSTRY —
SPECIFICATION

[Page 2, Table 1, Sl No. (v)] — Substitute the following for existing :

Sl No.	Characteristics	Requirement for		Method of Test	
		Raw Petroleum Coke (RPC)	Calcined Pet Coke (CPC)	Annexure	IS 1448/ ASTM D
(1)	(2)	(3)	(4)	(5)	(6)
v)	Volatile matter:			—	[P: 134] /D 7582
	a) percent by mass, <i>Min</i>	6	—		
	b) percent by mass, <i>Max</i>	16	0.4		