

AMENDMENT NO. 2 OCTOBER 1996
TO
IS 1305 : 1984 SPECIFICATION FOR GRAPHITE FOR
USE IN FOUNDRY COATINGS

(Third Revision)

(Page 8, clause B-5.3) — Substitute the following for the existing:

‘B-5.3 Calculation

$$\text{Non-graphitic carbon, percent by mass} = 100 \times \frac{(M_1 - M_2)}{M} - (A + B)$$

where

M_1 = first mass of the beaker and contents,

M_2 = second mass of the beaker and contents,

M = mass in g of the sample taken for test,

A = percent loss on heating (see B-2.1), and

B = percent petroleum ether soluble matter.’