

AMENDMENT NO. 1 JULY 2019
TO
IS 1343 : 2012 PRESTRESSED CONCRETE — CODE OF
PRACTICE
(Second Revision)

(Page 1, clause **3.12**) — Substitute the following for the existing clause:

‘3.12 Initial Prestress — The prestressing force in the tendon at transfer.’

(Page 1, clause **3.15**, line 4) — Substitute ‘during’ for ‘in’.

(Page 1, clause **3.17**) — Substitute the following for the existing clause:

‘3.17 Relaxation — Time dependent decrease in steel stress at constant strain.’

(Page 1, clause **3.18**) — Substitute the following for the existing clause:

‘3.18 Sheathing — A material encasing a prestressing tendon to prevent bonding the tendon with the surrounding concrete during placement of concrete and to provide protection against corrosion.’

[Page 3, clause **5.1**, Sl No. (a)] — Substitute the following for the existing:

‘a) Ordinary Portland cement conforming to IS 269,’

[Page 3, clause **5.1**(b) and (c)] — Delete.

(Page 3, clause **5.1**, para 2) — Insert the following at the end of para:

‘Rate of slow gain of strength with Portland slag cement and Portland pozzolana cement should be taken into account while deciding the de-shuttering time, curing period and the time of prestressing (*see also 11 and 14*).’

(Page 3, clause **5.2**) — Insert the following at the end of clause:

‘When mineral admixtures are used, rate of slow gain in strength should be taken into account while deciding the de-shuttering time, curing period and the time of prestressing (*see also 11 and 14*).’

Price Group 1

Amendment No. 1 to IS 1343 : 2012

(Page 8, clause **8.2.5.3**, line 4) — Insert ‘(where $\text{SO}_3 = 0.833 \text{ SO}_4$)’ after ‘ SO_3 ’.

(Page 9, Table 3, Note 4) — Substitute ‘col 7’ for ‘col 6’.

[Page 10, clause **8.2.5.4**, para 2, SI No. (b), line 3] — Substitute ‘[as Na_2O equivalent (expressed as $\text{Na}_2\text{O} + 0.658 \text{ K}_2\text{O}$)]’ for ‘(as Na_2O equivalent)’.

(Page 23, clause **14.1**, line 2) — Delete ‘and **14.1.2**’.

(Page 23, clause **14.1.1**) — Renumber the following clauses as follows:

- a) ‘**14.1.1.1**’ for ‘**14.1.2**’,
- b) ‘**14.1.1.2**’ for ‘**14.1.2.1**’,
- c) ‘**14.1.1.3**’ for ‘**14.1.2.3**’, and
- d) ‘**14.1.1.4**’ for ‘**14.1.2.4**’.

(Page 25, clause **19.5.2.3**, para 2) — Insert the following after para 2:

‘For periods less than 1 000 h, the value of relaxation losses (expressed as percent of 1 000 h value) shall be as shown below:

Time, h		1	5	20	100	200	500	1 000
Percent of Relaxation Loss at 1 000 h, %	For normal relaxation steel	34	44	55	70	78	90	100
	For low relaxation steel	37	47	57	72	79	90	100

[Page 26, clause **19.6.1.1** (c)] — Substitute ‘linearly’ for ‘parabolically’.

[Page 26, clause **19.6.1.1** (d)] — Delete.

Amendment No. 1 to IS 1343 : 2012

[Page 26, clause **19.6.2.1** (a), line 4] — Delete ‘relaxation of steel,’.

[Page 32, clause **23.4.1**, para 1) — Insert the following after para 1:

‘Where the position of a duct coincides with the position of maximum principal tensile stress, for example, at or near the junction of flange and the web near a support, the value of b should be reduced by the 1.2 times the diameter of duct if ungrouted metallic ducts or, grouted or ungrouted plastic ducts are used or in case of unbonded tendons and by half the diameter of the duct if grouted metallic ducts are used.’

(Page 38, Annex A) — Substitute the following for the existing entries for 269 : 1989, 383 : 1970, 455 : 1989, 875 (Part 3) : 1987, 1489, 3812 (Part 1) : 2003, 6006 : 1983 and 14268 : 1995:

<i>‘IS No.</i>	<i>Title</i>
269 : 2015	Ordinary Portland cement — Specification (<i>sixth revision</i>)
383 : 2016	Coarse and fine aggregate for concrete — Specification (<i>third revision</i>)
455 : 2015	Portland slag cement — Specification (<i>fifth revision</i>)
875 (Part 3) : 2015	Wind loads (<i>third revision</i>)
1489	Portland Pozzolana cement — Specification
(Part 1) : 2015	Fly ash based (<i>fourth revision</i>)
(Part 2) : 2015	Calcined clay based (<i>fourth revision</i>)
3812 (Part 1) : 2013	Pulverized Fuel Ash: Part 1 For use as Pozzolana in cement, cement mortar and concrete (<i>third revision</i>)
6006 : 2014	Uncoated stress relieved strand for prestressed concrete — Specification (<i>second revision</i>)
14268 : 2017	Uncoated stress relieved low relaxation seven-wire (Ply) strand for prestressed concrete — Specification (<i>first revision</i>)’

Amendment No. 1 to IS 1343 : 2012

[Page 38, *Annex A*, entries pertaining to ‘IS 8112 : 1989’ and ‘IS 12269 : 1987’] — Delete.

(Page 39, *clause B-2*, line 15) — Insert ‘/°C’ after ‘ 1.50×10^{-4} ’.