

**AMENDMENT NO. 1 FEBRUARY 1992
TO
IS 1344 : 1981 SPECIFICATION FOR CALCINED CLAY
POZZOLANA**

(Second Revision)

(Page 6, clause 5.3.1) — Insert the following new clause after 5.3.1:

'5.3.2 Differential thermal analysis technique may also be used for determination of calcination temperature at which the clay becomes reactive. In this technique the calcination temperature is determined from the completion of the endothermic peak which indicates loss of structural water (activation of clay).'