

AMENDMENT NO. 1 DECEMBER 1984

TO

IS : 1367 (Part VII) - 1980 TECHNICAL SUPPLY CONDITIONS FOR THREADED STEEL FASTENERS

PART VII MECHANICAL PROPERTIES AND TEST METHODS FOR NUTS WITHOUT SPECIFIED PROOF LOADS

(Second Revision)

(Page 1, Table 1) — Substitute the following for the existing table:

TABLE 1 DESIGNATION SYSTEM OF PROPERTY CLASSES			
Property Class	14 H	17 H	22 H
Vickers hardness, HV, Min	140	170	220

(Page 1, Table 2) — Substitute the following for the existing table:

TABLE 2 CHEMICAL COMPOSITION OF FORGED AND MACHINED (FROM OTHER THAN FREE CUTTING STEEL) NUTS				
Property Class	Chemical Composition Limits (Check Analysis)			
	Carbon, Max, percent	Manganese, Min, percent	Phosphorus Max, percent	Sulphur, Max, percent
14H	0.50	—	0.110	0.150
17H	0.58	0.30	0.060	0.150
22H*	0.58	0.30	0.048	0.058

*Nuts of property class 22H must be hardened and tempered in order to achieve the mechanical properties given in Table 4. If required, alloy steel may also be used.

(Page 2, Table 3, first column) — Substitute '14H, 17H' for '14H'.

(Page 2, Table 4) — Substitute the following for the existing table:

TABLE 4 MECHANICAL PROPERTIES			
Mechanical Properties	Property Class		
	14H	17H	22H
Vickers hardness HV5	140	170	220
Min hardness HV5 Max	220*	250	300

*260 Max for cold-forged nuts.

(Page 2, Explanatory Note, fourth para) — Delete ' IS : 8856-1978 Specification for hexagon weld nuts.'