

AMENDMENT NO. 1 APRIL 2006
TO
IS 1419 : 1989 ANTIFOULING PAINT, BRUSHING, FOR
SHIP'S BOTTOM AND HULLS — SPECIFICATION
(*Second Revision*)

(*Page 1, clause 5.3*) — Substitute the following for the existing clause:

'5.3 Relative Consistency

The efflux time for the first 50 ml of the material from Flow Cup No. 4 at $30 \pm 2^{\circ}\text{C}$, when determined as prescribed in IS 101 (Part 1/Sec 5) : 1989 shall be 30 to 50 seconds.'

(*Page 3, Annex A*) — Insert the following at the appropriate place:

'IS 101 (Part 1/ Sec 5) : Methods of sampling and test for paints, varnishes
1990 and related products : Part 1 Test on liquid paints
 (general and physical), Section 5 Consistency (*third*
 revision)'

(CHD 20)