

AMENDMENT NO. 1 NOVEMBER 2004
TO
IS 1448 (PART 147) : 1998 METHODS OF TEST FOR
PETROLEUM AND ITS PRODUCTS
[P : 147]
DETERMINATION OF POTENTIAL GUM IN MOTOR
GASOLINES

(Page 3, clause 12) — Substitute the following for the existing matter:

‘The result of two determinations on the same sample should not differ by more than the amount given below:

<i>Potential gum, g/m³</i>	<i>Repeatability</i>	<i>Reproducibility</i>
Up to 50	20	30
51 - 100	30	40
101 - 200	40	60