

AMENDMENT NO. 1 JULY 1988

TO

IS:1472-1977 METHODS FOR SAMPLING FERRO-ALLOYS
FOR DETERMINATION OF CHEMICAL COMPOSITION

(First Revision)

Sampling of Group III alloys has been elaborated in order to cater to different situations. A few modifications have been made in sample preparation procedures.

(Page 8, clause 5.2.3.2) - Substitute the following for the existing clause:

'5.2.3.2 Gross sample - When the material is supplied in wagons or trucks, the number of sub-lots shall be according to Table 1 and hence the entire consignment shall be divided into suitable number of wagons or trucks constituting sub-lots. Sampling shall be done from each sub-lot preferably when the material is in motion, that is, during loading or unloading. Suitable sample cutter shall be used for collecting material at regular intervals so that the gross sample so collected shall not be less than 100 kg in mass.'

5.2.3.3 Since these alloys are heavy and using a sampling scoop is not practical, the following method may preferably be used for collection of gross sample:

The material in one out of every five wagons or trucks or payloader buckets shall be opened on clean levelled ground in a single layer. The square frame of size on each side equal to at least three times the largest lump size shall be placed at random at one point on this layer and all those pieces which are completely inside and also which are at least

50 percent inside the frame shall be collected as one increment. From each selected wagons or trucks, at least two increments shall be collected in this fashion. However, the gross sample shall not be less than 100 kg in mass from each sub-lot.

5.2.3.4 When both the above methods are not possible, sampling may be done from stockpiles. For this purpose, trench sampling method may be used. By this method, material in a surface of 30-cm diameter cross section and over entire depth of stockpile shall be collected as one unit sample. If there are a number of stockpiles at least 25 percent of the stockpiles in the sub-lot shall be sampled in this manner ensuring that the minimum gross sample mass is satisfied.

5.2.3.5 Sampling from containers - When the alloys are supplied in containers, the sampling shall be done according to 5.3.3.'

(Page 8, clause 5.2.5) - Substitute 'Group V and Group VI Alloys' for 'Group VI Alloys'.

(Page 8, clause 5.2.5.1, line 2) - Substitute '5 000' for '10 000'.

(Page 9, clause 5.3.3.2) - Substitute the following for the existing clause:

'5.3.3.2 Gross sample - One out of every five containers shall be opened and content poured on a levelled ground. A gross sample of mass 100 kg shall be collected by the same procedure as in 5.2.3.2.'

(Page 10, clause 6.1.3, third sentence) - Substitute the following for the existing sentence:

'The 20 kg sample thus obtained shall be reduced by way of coning and quartering to not less than 500 g.

The sample so obtained shall be pulverised to pass through 150-micron sieve totally.'

(Page 11, clause 6.1.4, second sentence) -
Substitute the following for the existing sentence:

'All the drillings so obtained are mixed and passed through 500-micron sieve to remove drill bit contamination and then crushed in hardened alloy steel mortar to pass through 150-micron sieve.'

(SMDC 4)