

AMENDMENT NO. 1 MARCH 2024
TO
IS 10086 : 2021 MOULDS FOR USE IN TESTS OF CEMENT, CONCRETE AND
POZZOLANA — SPECIFICATION
(First Revision)

[Page 2, Table 2, col (2), Sl No. (iii)] — Add ‘, Min’ at the end.

[Page 3, Table 3, col (2), Sl No. (v)] — Add ‘, Min’ at the end.

[Page 3, Table 3, col (2), Sl No. (viii)] — Add ‘, Min’ at the end.

[Page 4, Table 4, col (2), Sl No. (iv)] — Add ‘, Min’ at the end.

[Page 4, Table 4, col (2), Sl No. (vii)] — Add ‘, Min’ at the end.

(Page 17, Table 6) — Substitute the following for existing:

‘Table 6 Additional Requirements for ABS Plastic Moulds

(Clause 6.1.2)

Sl No.	Model Type	Weight g, <i>Min</i>	Hardness Scale ¹ Shore D Value	Wall Thickness mm, <i>Min</i>
(1)	(2)	(3)	(4)	(5)
i)	50 mm × 50 mm × 50 mm cube mould	100	75 to 78	6
ii)	100 mm × 100 mm × 100 mm cube mould	530	75 to 78	9.5
iii)	100 mm × 100 mm × 100 mm 2-gang cube mould	950	75 to 78	9
iv)	150 mm × 150 mm × 150 mm cube mould	1 110	75 to 78	9.5
v)	50 mm × 50 mm × 50 mm 3-gang cube mould	820	75 to 78	6

(Page 18, Table 7) — Substitute the following for existing:

Price Group 1

¹⁾ Shore hardness value shall be determined as in IS 13360 (Part 5/Sec 11).

Amendment No. 1 to IS 10086 : 2021

Table 7 Additional Requirements for Rigid Polyurethane Moulds

(Clause 6.1.2)

Sl No.	Model Type	Weight g, <i>Min</i>	Hardness Scale ¹ Shore D value	Wall Thickness mm, <i>Min</i>	Density g/cm ³
(1)	(2)	(3)	(4)	(5)	(6)
i)	100 mm × 100 mm × 100 mm cube mould	440	60 to 62	12.5	0.40
ii)	150 mm × 150 mm × 150 mm cube mould	1 340	55 to 58	19	0.38
iii)	100 mm × 200 mm cylinder mould	830	60 to 62	15	0.45
iv)	100 mm × 100 mm 2-gang cube mould	890	55 to 58	19	0.45
v)	150 mm × 300 mm cylinder mould	1 940	45 to 50	25	0.32
vi)	100 mm × 100 mm × 500 mm beam mould	2 290	55 to 58	19	0.40
vii)	150 mm × 150 mm × 700 mm beam mould	3 990	55 to 58	25	0.40

(CED 02)

Publication, BIS, New Delhi

¹⁾ Density shall be determined as in IS 13360 (Part 3/Sec 10).