

AMENDMENT NO. 2 DECEMBER 2025
TO
IS 10086 : 2021 MOULDS FOR USE IN TESTS OF CEMENT, CONCRETE AND
POZZOLANA — SPECIFICATIONS
(First Revision)

(Page 17, Table 6) — Substitute the following for the existing:

Table 6 Additional Requirements for ABS Plastic Moulds

Sl No.	Model Type	Weight (in g), <i>Min</i>	Hardness Scale Shore D Value	Wall Thickness (mm), <i>Min</i>
(1)	(2)	(3)	(4)	(5)
(i)	50 × 50 × 50 mm cube mould	100	75 to 85	6.0
(ii)	100 × 100 × 100 mm cube mould	530	75 to 85	9.5
(iii)	100 × 100 × 100 mm 2-gang cube mould	950	75 to 85	9.0
(iv)	150 × 150 × 150 mm cube mould	1 110	75 to 85	9.5
(v)	50 × 50 × 50 mm 3 gang cube mould	820	75 to 85	6.0

(Page 18, Table 7) — Substitute the following for the existing:

Table 7 Additional Requirements for Rigid Polyurethane Moulds

Sl No.	Model Type	Weight (in gm), <i>Min</i>	Hardness Scale Shore D Value	Wall Thickness (in mm), <i>Min</i>	Density (in g/cm ³)
(1)	(2)	(3)	(4)	(5)	(6)
(i)	100 × 100 × 100 mm cube mould	440	58 to 68	12.5	0.40
(ii)	150 × 150 × 150 mm cube mould	1 340	54 to 64	19	0.38
(iii)	100 × 200 mm cylinder mould	830	58 to 68	15	0.45
(iv)	100 × 100 mm 2-gang cube mould	890	54 to 64	19	0.45
(v)	150 × 300 mm cylinder mould	1 940	45 to 55	25	0.32
(vi)	100 × 100 × 500 mm beam mould	2 290	54 to 64	19	0.40
(vii)	150 × 150 × 700 mm beam mould	3 990	65 to 75	25	0.40

(CED 02)

Price Group 1
Publication, BIS, New Delhi