

**AMENDMENT NO. 2 NOVEMBER 2007
TO
IS 9968 (PART 2): 2002 SPECIFICATION FOR
ELASTOMER — INSULATED CABLES**

**PART 2 FOR WORKING VOLTAGES FROM 3.3 kV UP TO
AND INCLUDING 33 kV**

(First Revision)

(Page 1, clause 2) — Substitute 'Low carbon galvanized steel wires, formed wires and tapes for armouring of cables — Specification *(third revision)*' for the existing title of IS 3975 1999

(Page 3, clause 20.2.1, last line) — Add the following matter at the end

"The tolerance on nominal dimensions shall be as per IS 3975 However, for formed steel wires compliance shall be ensured only for dimensions 'A' & 'C' "

(Page 4, clause 20.2 2, para 2) — Substitute the following for the existing matter

Diameter of braiding wires shall be in accordance with Table 6 The tolerance on nominal dimensions shall be as per IS 3975 '

(Page 4, clause 20 3) — Insert the following new clause after 20.3.

'20.4 The round steel wires/formed steel wires taken from the cable shall meet the following requirements

- a) The tensile strength of round steel wire/formed steel wire shall be not less than 250 N/mm² and not more 580 N/mm²
- b) The Elongation at break of round steel wire/formed steel wire shall be not less than 6 percent
- c) Round steel wire shall meet the requirements of torsion test The gauge length between Vices and the minimum number of turns without break shall be as per Table 6 of IS 3975
- d) The zinc coating shall not show any cracks and shall not flake off on rubbing by the bare finger when the formed steel wire is subjected to winding test

Amend No 2 to IS 9968 (Part 2) : 2002

- e) The uniformity of zinc coating of round steel wire/formed steel wire shall comply with the requirements of IS 3975 subject to the following
 - The minimum number of dips shall be reduced by one half-minute dip
 - In case of formed wires, dip test is applicable only for the face
- f) The mass of zinc coating of round steel wire shall be not less than 95 percent of the mass specified in Table 2 of IS 4826 The mass of zinc coating of formed steel wire shall be not less than 95 percent of the mass specified in IS 3975
- g) The resistivity of the round steel wire/formed steel wire shall meet the requirements of IS 3975 '

[Page 5, clause **22 1**, *Sl No* (b)] — Substitute the following for the existing

- b) Tests for round steel wire/formed steel wire (strip) armour
 - 1) Dimensions **20.2.1 & 20.2 2** of IS 9968 (Part 2) Part 36 of IS 10810
 - 2) Physical tests on round/formed wire
 - i) Tensile strength **20 4(a)** of IS 9968 (Part 2) Part 37 of IS 10810
 - ii) Elongation at break **20.4(b)** of IS 9968 (Part 2) Part 37 of IS 10810
 - iii) Torsion test for round wires **20 4(c)** of IS 9968 (Part 2) Part 38 of IS 10810
 - IV) Winding test for formed wires **20.4(d)** of IS 9968 (Part 2) Part 39 of IS 10810
 - v) Uniformity of zinc coating **20.4(e)** of IS 9968 (Part 2) Part 40 of IS 10810
 - vi) Mass of zinc coating **20.4(f)** of IS 9968 (Part 2) Part 41 of IS 10810
 - vii) Resistivity **20.4(g)** of IS 9968 (Part 2) Part 42 of IS 10810

(ET 09)