

**AMENDMENT NO. 1 MAY 2002
TO
IS 3589 : 2001 STEEL PIPES FOR WATER AND
SEWAGE (168.3 TO 2 540 mm OUTSIDE DIAMETER) —
SPECIFICATION**

(Third Revision)

[Page 1, clause 4.1(a), line 1] — Substitutue 'quantity' for 'quality'.

(Page 3, Table 2) — Substitute the following for the existing table:

Table 2 Chemical composition
(Clauses 8.1 and 8.2)

Steel Grade	Method of Manufacture	Chemical Composition (Ladle Analysis)				
		C	Mn	P	S	CE
		Max	Max	Max	Max	Max
Fe 330	Seamless (S)	0.16	1.20	0.040	0.040	—
Fe 330	Welded (ERW)	0.16	1.20	0.040	0.040	—
Fe 330	Welded (SAW)	0.16	1.20	0.040	0.040	—
Fe 410	Seamless (s)	0.20	1.30	0.040	0.040	0.45
Fe 410	Welded (ERW)	0.20	1.30	0.040	0.040	0.45
Fe 410	Welded (SAW)	0.20	1.30	0.040	0.040	0.45
Fe 450	Seamless(s)	0.25	1.20	0.040	0.040	0.45
Fe 450	Welded (ERW)	0.25	1.20	0.040	0.040	0.45
Fe 450	Welded (SAW)	0.25	1.30	0.040	0.040	0.45

(Page 5, clause 11.1.1) — Substitute the following for the existing formula:

$$M = (D - T) \times T \times 0.024\ 661\ 5$$

(Page 6, Table 5, column 6, OD 1067 mm, thickness 11.0 mm) —
Substitute '286' for '186' mass in kg/m.

(Page 8, Table 7) — Substitute the following for the existing table:

