

AMENDMENT NO. 3 SEPTEMBER 2003
TO
IS 3736 : 1995 CANVAS BOOTS, RUBBER SOLE —
SPECIFICATION
(Second Revision)

(Page 1, clause 4.1.1) — Substitute the following for the existing:

'4.1.1 Upper

The upper shall consist of Rip Stop Fabric of cotton or manmade or its blend being the over layer and cotton drill as an inner layer and shall conform to the requirements given at Sl No. (i) of Table 1.???

Two fabrics shall be adhered together with rubber compound so as to achieve the requirements as prescribed for consolidation test and composite upper material strength test

Higher value of over layer and inner layer fabric can also be used as agreed to between the manufacturer and the purchaser to meet the special requirements of performances.

Shade of over layer will be agreed to between the purchaser and the manufacturer.'

(Page 1, Table 1, Sl No. 1) — Substitute the following for the existing:

Table 1 Requirements for Overlayer and Inner Layer

Sl No.	Material	Characteristics	Requirement	Method of Test Ref to IS No.
(1)	(2)	(3)	(4)	(5)
i)	Overlayer	Construction	Rip Stop	
		Breaking load in N.Min (5 × 20 cm grip):		IS 1969
		a) Wrap	1 650	
		b) Weft	1 350	
		c) Ends/dm	220 ± 5 (2 ply)	IS 1963
		d) Picks/dm	150 ± 5 (2 ply)	

Amend No. 3 to IS 3736 : 1995

(Page 1, clause 4.1.3, line 1) — Substitute 'Cotton, man made or blended material' for 'Cotton tape NEWAR'.

(Page 2, clause 4.1.5.1) — Substitute the following for the existing:

4.1.5.1 Sewing thread cotton, man made or blended shall be used for stitching of upper. For cotton variety thread shall conform to variety No. 28 of IS 1720. Polyester variety thread shall conform to variety No. 9 of IS 9543.

Any other blend of thread would have breaking load not less than above referred requirements.

Sewing thread cotton, manmade or blended shall be used for binding of upper. For cotton variety thread shall conform to variety No. 32 of IS 1720. Polyester variety thread shall conform to variety No. 5 of IS 9543.

Any other blend of thread would have breaking load not less than above referred requirement of specification.'

(Page 2, clause 4.1.6.1, lines 1 and 2) — Insert the words 'of cotton or man made or blended' between 'braided' and 'fabric'.

(Page 5, clause 4.4.4, line 1) — Delete the word 'seams'.

(Page 5, clause 4.4.6) — Substitute the following for the existing:

4.4.6 A minimum of seven aluminium, brass or steel eyelets having 10 mm diameter and wall thickness 0.30 to 0.35 mm shall be fitted in each face.'

(Page 5, clause 4.4.7, last line) — Substitute 'top edge with white cloth for binding of counter' for 'top edge with white cloth cotton bias binding'.

(Page 5, clause 4.4.9) — Insert the following sentence at the end:

'This is not required when the same is produced in direct moulded construction.'

(Page 6, clause 4.8) — Insert the following clause after 4.8:

4.9 Composite Breaking Strength Test

From the upper of made up footwear representative sample of width 25 ± 0.5 mm width strip is to be cut along the length of the boot of enough length so as to make it convenient to allow a distance of minimum 30 mm between the jaws of the tensile machine.

Amend No. 3 to IS 3736 : 1995

Rate of traverse of pulling jaw shall be 100 ± 5 mm per minute.

Two such test pieces will be required to be obtained from the made up footwear and will be subjected to test to break each test piece.

Mean value of each set of test pieces comprising of length wise and height wise test pieces will be 1 000 N/25 mm width minimum.'

(CHD 19)