

AMENDMENT NO. 1 SEPTEMBER 2021

TO

IS 3771 : 2019 TEXTILES — LONG CLOTH, COTTON KHADI, BLEACHED — SPECIFICATION

(*Second Revision*)

(Page 1, Table 1) — Substitute the following for the existing:

**‘Table 1 Constructional Particulars and Breaking Load Requirements
for Long Cloth, Cotton Khadi, Bleached**

(*Clauses 4.1 and 5.1*)

(1)	Count of Yarn (for Guidance only) Universal Count (Cotton Count)		Ends/dm	Picks/dm	Mass, g/m ²	Breaking Load (on 10.0 × 20 cm Strips), N	
	Warp	Weft				Warp	Weft
(2)	(3)	(4)	(5)	(6)	(7)	(8)	
	37 tex (16 ^s)	49 tex (12 ^s)	174	174	160	392	372
Tolerance, percent	—	—	± 5	± 10	± 10	-10	-10
← (see Note) →							
Method of Test	IS 3442	IS 3442	IS 1963	IS 1963	IS 1964	IS 1969 (Part 1)	IS 1969 (Part 1)

NOTE — Any increase in values of mass (g/m²) or breaking load beyond positive tolerance shall not be a cause of rejection of the fabric.