

AMENDMENT NO. 2 MAY 2004
TO
IS 3846 : 1984 SPECIFICATION FOR ROT-PROOFED
COTTON TAPES FOR AEROSPACE PURPOSES
(*First Revision*)

(*Page 4, clause 3.4.1*) — Substitute the following for the existing:

'3.4.1 The tapes shall be rot-proofed with pentachlorophenyl laurate (PCPL) from aqueous emulsions in accordance with IS 11662 : 1986 Specification for preservative treatment of textiles. The PCPL content shall not be less than 3.5 percent on oven dry mass of the tape when tested by the method prescribed in Appendix E. However, if agreed to between the buyer and the seller any other rot-proofing agent may also be used.'

(TX 13)

Reprography Unit, BIS, New Delhi, India