

AMENDMENT NO. 1 SEPTEMBER 1969
TO
IS : 3878-1967 SPECIFICATION FOR PLASTER
SHEARS, DENTAL

Alterations

(*First cover page, pages 1 and 2, Title*) — Substitute the following for the existing title:

' Indian Standard

SPECIFICATION FOR SHEARS, PLASTER, DENTAL '

(*Page 3, clause 6.1*) — Substitute the following for the existing clause:

'6.1 Performance Test — The plaster shears shall cut a slab 20 mm thick of set stone-plaster. The test shall be repeated ten times. There shall be no damage to the shears or cutting edges after the completion of the test. The stone-plaster slab shall be prepared as detailed in 6.1.1.'

(*Page 4, Fig. 1*)

a) Add the following dimension to the existing figure:

'Radius of curvature of the cutting jaws = 43 mm'

b) Substitute the following for the existing caption of the figure:

' FIG. 1 SHEARS, PLASTER, DENTAL '

(*Page 5, clause 6.1.1*) — Delete.

(*Page 5, clause 6.1.2*) — Substitute the following for the existing clause:

'6.1.1 Stone-Plaster Slab — Mix 100 g of stone-plaster powder ($\text{CaSO}_4 \cdot \frac{1}{2} \text{H}_2\text{O}$ known as α calcium sulphate hemihydrate) with 20 to 28 ml of water at room temperature. The mixture shall be spatulated with the help of a plaster spatula for a period of 2 minutes so that it attains a smooth creamy mix and then vibrated to eliminate the air bubbles. The mixture shall be poured into the cast and again vibrated to further eliminate the air bubbles and then allowed to set for a period of 15 to 20 minutes. The cast shall then be taken out and dried till it attains a compressive strength of 600 kgf/cm².'