

AMENDMENT NO. 1 APRIL 1995
TO
IS 3885 (Part 2) : 1992 STEEL FOR THE MANUFACTURE OF
LAMINATED SPRINGS (RAILWAY ROLLING STOCK)
PART 2 RIB AND GROOVE SECTIONS
(Second Revision)

(Page 2, Table 1) – Substitute the following for the existing table:

Table 1 Chemical Composition
(Clauses 3.1 and 6.1)

Grade	Designation [see IS 1762 (Part 1) : 1974*]	Type	Constituent, Percent							
			Carbon	Silicon	Manganese	Sulphur Max	Phosphorus Max	Chromium	Vanadium	Molybde- num
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
1	55C6	Water-hardening	0.50 to 0.60	0.15 to 0.30	0.50 to 0.60	0.050	0.050	—	—	—
2	75C6	Oil-hardening	0.70 to 0.80	0.15 to 0.35	0.50 to 0.80	0.050	0.050	—	—	—
3	40Si7	Water-hardening	0.35 to 0.45	1.50 to 2.00	0.80 to 1.00	0.030	0.030	—	—	—
4	55Si7	Oil-hardening	0.50 to 0.60	1.50 to 2.00	0.80 to 1.00	0.030	0.030	—	—	—
5	50Cr4V2	Oil-hardening	0.45 to 0.55	0.15 to 0.35	0.50 to 0.80	0.030	0.030	0.90 to 1.20	0.15 to 0.30	—
6	60Cr4V2	Oil-hardening	0.55 to 0.65	0.15 to 0.35	0.80 to 1.00	0.030	0.030	0.90 to 1.20	0.15 to 0.30	—
7	51CrMoV	Oil-hardening	0.48 to 0.56	0.15 to 0.40	0.70 to 1.10	0.030	0.030	0.90 to 1.20	0.07 to 0.12	0.15 to 0.25

* Code for designation of steel : Part 1 Based on letter symbols (first revision).

(Page 2, clause 9.1, line 2) – Substitute ‘2.0’ for ‘2.5’.

(Page 2, Table 2, headed under Grade) – Substitute ‘51CrMoV’ for ‘51CrMoV4’.

(Page 4, clause 15.1) – Substitute the following for the existing clause:

"15.1 The material shall be supplied in ‘as rolled’ condition."