

AMENDMENT NO. 2 DECEMBER 1984

TO

IS : 2998-1982 SPECIFICATION FOR COLD FORGED STEEL RIVETS FOR COLD CLOSING (1 to 16 mm DIAMETER)

(*First Revision*)

Corrigenda

(Page 1, clause 5.4) — Substitute the following hardness values for Grade 1 and Grade 2:

Grade 1 — 56 to 78 HRB (100 - 139 VPN)

Grade 2 — 48 to 73 HRB (91 - 127 VPN)

(Page 2, Table 1) — Under *d Nom 1.2*, for *d_k Min* substitute ' 1.72 ' for ' 1.82 '.

Alterations

(Pages 3, 4 and 5 and Tables 2, 3 and 4) — Substitute the following values for *d_k Min* for the sizes given below:

<i>d</i>	1.2	(1.4)	(3.5)	4.0	5.0	6.0	7.0	8.0	10	12	14	16
	2.15	2.55	6.42	7.42	9.42	11.3	13.3	15.3	19.16	23.16	27.16	31
<i>d_k Min</i>	<i>for</i>	<i>for</i>	<i>for</i>	<i>for</i>	<i>for</i>	<i>for</i>	<i>for</i>	<i>for</i>	<i>for</i>	<i>for</i>	<i>for</i>	<i>for</i>
	2.25	2.65	6.64	7.64	9.64	11.57	13.57	15.57	19.48	23.48	27.48	31.38

(Page 6, Table 5, 1st column) — Substitute

$$\begin{array}{l} +0.5 \\ -0 \end{array} \text{ for } l \leq 10 \quad \text{for} \quad \begin{array}{l} +0.5 \\ 0 \end{array} \text{ FOR } d \leq 10$$

$$/ \text{ TOL } \begin{array}{l} +1.0 \\ 0 \end{array} \text{ for } 10 < l \leq 20 \quad \text{' / Tol } \begin{array}{l} +1.0 \\ 0 \end{array} \text{ FOR } d > 10 '$$

$$+1.5 \\ 0 \end{array} \text{ for } l > 20 '$$