

AMENDMENT NO. 1 MARCH 2011
TO
IS 3005 (PART 1) : 1979 SPECIFICATION FOR GREY CAST IRON INGOT
MOULDS, STOOLS AND SLAG LADLES

PART 1 BOTTOM STOOLS FOR LARGE SIZE INGOT MOULDS WEIGHING 8 TONNES AND
HIGHER

(First Revision)

(Page 4, clause 3.1) — Substitute 'IS 228†' for 'IS : 228 - 1959†'.

(Page 4, clause 3.1, informal table, row 1) — Substitute the following for the existing:

<i>Constituent</i>	<i>Percent</i>
Carbon	3.4 to 3.6

(Page 4, informal table, row 4, col 2) — Substitute '0.18' for '0.3'.

(Page 4, footnote marked †) — Substitute the following for the existing:

'Methods of chemical analysis of pig iron, cast iron and plain carbon and low alloy steels (*revised*) (issued in parts).'

(Page 6, clause 7.1, line 2) — Substitute '36 hours' for '48 hours'.

(Page 6, clause 8.1) — Add the following sentence at the end:

'No welding is permitted.'

(Page 6, clauses 8.2 to 8.5) — Delete.

*(Page 6, footnote marked *)* — Delete.

(Page 7, clause 13.2.1) — Substitute the following for the existing:

'13.2.1 BIS Certification Marking

Each stool may also be marked with the Standard Mark.

Amend No. 1 to IS 3005 (Part 1) : 1979

13.2.1.1 The use of the Standard Mark is governed by the provisions of the *Bureau of Indian Standards Act, 1986* and the Rules and Regulations made thereunder. The details of conditions under which the licence for the use of Standard Mark may be granted to manufacturers or producers, may be obtained from the Bureau of Indian Standards.'

(MTD 6)