

AMENDMENT NO. 1 APRIL 2011
TO
IS 3005 (PART 4) : 1984 SPECIFICATION FOR GREY CAST
IRON INGOT MOULDS, STOOLS AND SLAG LADLES

PART 4 GREY CAST IRON INGOT MOULDS
OF MASS UP TO 1 TONNE

(First Revision)

(Page 4, clause 2.1) — Substitute the following for the existing:

‘The grades of grey iron ingot moulds shall be as per IS 210 : 1993§’ and add a footnote as follows:

‘§Grey iron castings (*fourth revision*).’

(Page 4, clause 3.1) — Substitute ‘IS 1387 : 1993†’ for ‘IS : 1387-1967†’.

(Page 4, clause 5.1) — Substitute ‘IS 228‡’ for ‘IS : 228-1959‡’.

(Page 4, Table 1, row 1) — Delete.

(Page 4, Table 1, row 2) — Substitute ‘Carbon 3.6-3.8’ for ‘Total carbon 3.2-3.4’.

(Page 4, Table 1, row 4, col 2) — Substitute ‘1.4-1.8’ for ‘1.2-1.8’.

(Page 4, Table 1, row 7, col 2) — Substitute ‘0.18’ for ‘0.30’.

(Page 4, footnote marked †) — Substitute ‘(*second revision*)’ for ‘(*first revision*)’.

(Page 4, footnote marked ‡) — Substitute the following for the existing:

‘Methods of chemical analysis of pig iron, cast iron and plain carbon and low alloy steels (*revised*) (issued in parts).’

(Page 5, clause 10.1, line 1) — Substitute ‘6 hours’ for ‘4 hours’.

Amend No. 1 to IS 3005 (Part 4) : 1984

(Page 5, clause 10.1, line 2) — Delete the sentence ‘Pencil ingot may be stripped after 3 hours’.

(Page 6, clause 14.1) — Substitute the following for the existing:

‘No grinding and welding rectification of inside surface shall be permitted.’

(Page 9, clause 21.2) — Substitute the following for the existing:

‘21.2 BIS Certification Marking

Each material may also be marked with the Standard Mark.

21.2.1 The use of the Standard Mark is governed by the provisions of the *Bureau of Indian Standards Act*, 1986 and the Rules and Regulations made thereunder. The details of conditions under which the licence for the use of Standard Mark may be granted to manufacturers or producers, may be obtained from the Bureau of Indian Standards.’