

AMENDMENT NO. 4 DECEMBER 1986
TO
IS : 3073-1967 ASSESSMENT OF SURFACE
ROUGHNESS

[One more sampling length suitable for different types of machined surfaces was included in Table 3 of this standard through Amendment No. 3. Inadvertently the values were wrongly represented which have now been rectified through this amendment.]

[(Page 10, Table 3 (see also Amendment No. 3)) — Substitute the following for the existing table:

TABLE 3 SUITABLE SAMPLING LENGTHS FOR VARIOUS MACHINING SURFACES

PROCESS	SUITABLE SAMPLING LENGTHS, mm						
Milling	—	—	0.8	2.5	8	10	—
Boring	—	—	0.8	2.5	8	10	—
Turning	—	—	0.8	2.5	—	—	—
Grinding	—	0.25	0.8	2.5	—	—	—
Planing	—	—	—	2.5	8	10	25
Reaming	—	—	0.8	2.5	—	—	—
Broaching	—	—	0.8	—	—	—	—
Diamond boring	—	0.25	0.8	—	—	—	—
Diamond turning	—	0.25	0.8	—	—	—	—
Honing	0.08	0.25	0.8	—	—	—	—
Lapping	0.08	0.25	0.8	—	—	—	—
Superfinishing	0.08	0.25	0.8	—	—	—	—
Buffing	—	—	0.8	2.5	—	—	—
Polishing	—	—	0.8	2.5	—	—	—
Shaping	—	—	0.8	2.5	8	10	—
Spark machining	—	—	0.8	—	—	—	—