

AMENDMENT NO. 3 AUGUST 2019
TO
IS 3196 (PART 1) : 2013 WELDED LOW CARBON STEEL
GAS CYLINDERS EXCEEDING 5 LITRES WATER
CAPACITY FOR LOW PRESSURE LIQUEFIABLE
GASES

PART 1 CYLINDERS FOR LIQUEFIED PETROLEUM GASES
(LPG) — SPECIFICATION

(Sixth Revision)

(Page 9, clause 23.2) — Substitute the following for the existing clause:

‘23.2 The outside surface shall be grit (*see* IS 4683) blasted with minimum SA 2.5 grade of blast (*see* IS 9954) and shall be given following protective coatings:

- a) Spraying zinc to give a coating of minimum thickness of 37 microns unless otherwise agreed to between the purchaser and the manufacturer. The zinc wire used for spraying shall be as per IS 12447 and the zinc spraying shall be as per IS 6586;
- b) One coat of primer as per IS 2074 (Part 1) or IS 12744 (Part 1) shall be used in case of enamel paint. If cylinder is painted with polyurethane paint, one coat of epoxy primer as per IS 13238 shall be used. Colour of the primer shall be as agreed to between the purchaser and the manufacturer. Any other primer may be used as per agreement between the manufacturer and the purchaser with approval of Statutory Authority;
- c) One coat of synthetic enamel paint conforming to IS 2932 (Part 1) or polyurethane paint conforming to IS 13213, of signal red colour (Shade No. 537 of IS 5) or any other colour as approved by statutory authority. Both the layers of the primer and paint shall have a total thickness of minimum 30 microns. Any other paint may be used as per agreement between the manufacturer and the purchaser with approval of Statutory Authority;
- d) As an alternate to (b) and (c) above, cylinders shall be powder coated conforming to IS 13871 of signal red colour (Shade No. 537 of IS 5) or any other colour as approved by statutory authority. Powder coating shall have a thickness of minimum 30 microns.
- e) The total combined thicknesses of above protective coatings shall be minimum 67 microns.

Amendment No. 3 to IS 3196 (PART 1) : 2013

NOTE — Procedure for measurement of coating of thickness:

- a) Five gauge readings for each spot shall be taken moving the probe a short distance for each new gauge reading within an approximate area of 2 cm × 2 cm. Discard any unusually high or low gauge reading that can not be repeated consistently. Take the average of the five gauge readings as a spot measurement.
- b) Make five such spot measurements approximately evenly spaced over the surface of the cylinder.
- c) Each spot measurement shall not be below 80 percent of the specified minimum thickness and average of the five spot measurements shall not be below the specified thickness.'

(Page 10, Annex A) — Substitute 'IS 2074 (Part 1) : 2015 Ready mixed paint, air drying, red oxide — Zinc chrome, priming — Specification : Part 1 For domestic and decorative applications (*third revision*)' for 'IS 2074 : 1992 Ready mixed paint, air drying, red oxide zinc chrome, priming (*second revision*)'.

(Page 10, Annex A) — Substitute 'IS 2932 (Part 1) : 2013 E namel, synthetic, exterior: (a) undercoating (b) finishing — Specification Part 1 For domestic and decorative applications (*fourth revision*)' for 'IS 2932 : 2003 Enamel, synthetic, exterior (a)undercoating, (b) finishing — Specification (*third revision*)'.

(Page 10, Annex A) — Insert the following new entries at an appropriate places:

<i>'IS No.</i>	<i>Title</i>
2931 (Part 1) : 2013	Ready mixed paint, air drying, red oxide — Zinc phosphate, priming — Specification: Part 1 For domestic and decorative applications (<i>first revision</i>)
12744 (Part 1) : 2013	Ready mixed paint, air drying, red oxide — Zinc phosphate, priming — Specification: Part 1 For domestic and decorative applications
13213 : 2018	Polyurethane full gloss enamel (two pack) — Specification (<i>first revision</i>)
13238 : 1991	Epoxy based zinc phosphate primer (two pack) — Specification'