

**AMENDMENT NO. 1 MARCH 2003
TO
IS 3196 (PART 4) : 2001 WELDED LOW CARBON
STEEL CYLINDERS EXCEEDING 5 LITRE WATER
CAPACITY FOR LOW PRESSURE LIQUEFIABLE
GASES**

PART 4 CYLINDERS FOR TOXIC AND CORROSIVE GASES

(*Page 7, clause 18.1.1*) — Insert '18.1.7' after '18.1.6' in third line.

(*Page 9, clause 18.1.6*) — Insert the following **new clause 18.1.7** after **18.1.6**:

18.1.7 Macro Examination — The macro-etching of a complete cross section of the weld shall show a good penetration and absence of lack of fusion, significant inclusions and other defects. In case of doubt, a micro-etching of the doubtful zone shall be investigated.'

(ME 16)