

AMENDMENT NO. 1 APRIL 1982

TO

IS:5640-1970 METHOD OF TEST FOR DETERMINING AGGREGATES
IMPACT VALUE OF SOFT COARSE AGGREGATES

Alteration

(Page 5, clause 3.1, second sentence) - Substitute
the following for the existing sentence:

'The aggregate comprising the test sample shall be dried
in an oven at a temperature of 105 to 110°C for a period
of four hours and cooled, until the weight becomes'
constant.'

(BDC 6)

Reprography Unit, BIS, New Delhi, India