

AMENDMENT NO. 1 JANUARY 2023

TO

IS 5656 : 2021 TEXTILES — COTTON BRAIDS FOR SLEEVING — SPECIFICATION (First Revision)

(Page 1, Table 1) — Substitute the following for the existing:

Table 1 Physical Requirements of Cotton Braids
(Clause 4.2)

Sl No.	Type	Variety No.	Flat width, mm	Diameter, mm	No. of Yarns per Strand		No. of Strands		Plaits per 30 cm	Weight per 100 m, g	Breaking Load on Full width × 20 cm Test Length, kgf, <i>Min</i>
					Braid	Core	Braid	Core			
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)
i)	With Core	┌ 1	—	1.5	2	2	12	3	38	95	10
ii)		├ 2	—	2	2	2	12	2	35	110	12
iii)		└ 3	—	3	2	2	16	2	28	160	19
iv)	Without Core	┌ 4	6	—	2	—	32	—	12	220	29
v)		├ 5	6.5	—	2	—	40	—	10	270	31
vi)		└ 6	8	—	2	—	48	—	9	330	42
Tolerance		—	± 0.5	± 0.5	—	—	—	—	± 2	± 10	—
Method of Test		—	B-2	B-2	B-3	B-3	B-4	B-5	—	—	IS 1969 (Part 1)