

AMENDMENT NO. 1 NOVEMBER 1980
TO
IS : 5731-1970 SPECIFICATION FOR ANTIMONY SULPHIDE
FOR EXPLOSIVE AND PYROTECHNIC COMPOSITIONS

Alterations

(*Page 14, clauses A-9.1 to A-9.3*) - Substitute
the following for the existing clauses:

'A-9.0 General - Grit is that portion of the material which is insoluble in aqua regia and 50 percent sodium hydroxide solution and is retained on 125-micron IS Sieve and is capable of scratching soda glass.

A-9.1 Reagents

A-9.1.1 *Sodium Hydroxide Solution* - Dissolve 50 g of sodium hydroxide in 100 ml of water.

A-9.1.2 *Dilute Hydrochloric Acid* - 2 percent (v/v).

A-9.2 Procedure - Boil the matter insoluble in aqua regia obtained in A-8.2 for about 10 minutes with 20 ml of sodium hydroxide solution. Dilute immediately with 200 to 300 ml of water, wash the gritty matter three times with water by decantation and then once with dilute hydrochloric acid. Filter on Whatman filter paper No. 40 or equivalent. Wash, ignite gently, cool and weigh till constant mass is obtained.

A-9.2.1 Brush the ignited matter on 125-micron IS Sieve and weigh the portion retained. Carry out the soda glass scratching test as prescribed in A-9.4. If the residue scratches soda glass, express the mass (previously obtained) as percentage grit.

A-9.3 Calculation,

$$\text{Grit, percent by mass} = 100 \times \frac{M_1}{M}$$

where

M_1 = mass in g of the grit retained on the sieve, and

M = mass in g of the material taken for the test.

A-9.4 Soda Glass Scratching Test - Take a portion of the residue, retained on 125-micron IS Sieve, in between two clean glass slides and press/slide them by hand along the length and breadth of the glass. Examine whether any scratch on the glass is obtained. If there is a scratch in the glass, then the residue is termed as grit.'

(CC 51)