

AMENDMENT NO. 1 JANUARY 1988

TO

IS:5787-1986 SPECIFICATION FOR SPHEROIDAL OR
MODULAR GRAPHITE IRON CASTINGS FOR PAPER
MILL DRYER ROLLS

(First Revision)

(Page 4, clause 4.1) - Substitute the following for the existing clause:

'4.1 The chemical composition of the castings when determined in accordance with the methods specified in IS:228-1959* and/or any of its relevant part or by any other established instrumental/chemical method, shall be as given below:

<u>Constituent</u>	<u>Percent</u>
Total carbon, <u>Min</u>	3.0
Silicon, <u>Max</u>	3.0
Phosphorus, <u>Max</u>	0.08
Carbon equivalent	3.8 to 4.5
[Total C + 0.3 (Si + P)]	

In case of dispute the procedure specified in IS:228-1959* or in its relevant part shall be the referee method.'

*Method of chemical analysis of pig iron, cast iron and plain carbon and low alloy steels (revised).

(SMDC 9)