

AMENDMENT NO. 1 NOVEMBER 1987

TO

IS:5788-1986 SPECIFICATION FOR IRON CASTINGS WITH
SPHEROIDAL OR NODULAR GRAPHITE FOR PRESSURE
CONTAINING PARTS FOR USE AT
ELEVATED TEMPERATURES

(First Revision)

(Page 4, clause 4.1) - Substitute the following for the existing clause:

'4.1 The chemical composition of the castings when determined in accordance with the methods specified in IS:228-1959* and/or any of its relevant part or by any other established instrumental/chemical method, shall be as given below:

<u>Constituent</u>	<u>Percent</u>
Total carbon, <u>Min</u>	3.0
Silicon, <u>Max</u>	2.50
Phosphorus, <u>Max</u>	0.08

In case of dispute the procedure specified in IS:228-1959* or in its relevant part shall be the referee method.

Note 1 - For each reduction of 0.01 percent below the maximum specified phosphorus content, an increase of 0.08 percent silicon above the specified maximum will be permitted up to a maximum of 2.75 percent.

Note 2 - Silicon content above 2.75 percent, or phosphorus above 0.08 percent have a tendency to lower the impact resistance of the material. If the carbon content is below 3.0 percent, excessive cementite may form during cooling and if this is not removed during the annealing cycle, the impact resistance of the material may be lowered.'

*Method of chemical analysis of pig iron, cast iron and plain carbon and low alloy steels(revised).

(SMDC 9)