

**AMENDMENT NO. 1 SEPTEMBER 2007
TO
IS 5817 : 1992 PREPARATION AND USE OF
LIME-POZZOLANA MIXTURE CONCRETE
IN BUILDINGS AND ROADS —
CODE OF PRACTICE**

(First Revision)

(Page 1, clause 4.4) — Substitute the following for the existing clause

‘4.4 Fine Aggregate

Fine aggregate for use in lime-pozzolana mixture concrete shall conform to IS 383 Aggregate conforming to IS 2686, having the required grading for fine aggregate as laid down in IS 383 may also be used Pulverized fuel ash conforming to IS 3812 (Part 2) having required grading may also be used as part of fine aggregate ’

(Page 1, clause 4.5) — Substitute the following for the existing clause

‘4.5 Water

Water used for mixing and curing lime-pozzolana mixture concrete shall conform to the requirement given in 5.4 of IS 456 ’

[Page 1, clause 5.1(f)] — Substitute the following for the existing

‘For making paving blocks including tiles and solid/hollow building blocks ’

(Page 6, Annex A) — Include the following new standard ‘IS 456’ alongwith its title and substitute the following for IS 3182 1986 alongwith its title

<i>IS No</i>	<i>Title</i>
IS 456 2000	Plain and reinforced concrete — Code of practice (<i>fourth revision</i>)
IS 3812 (Part 2) 2003	Pulverized fuel ash — Specification Part 2 For use as admixture in cement mortar and concrete (<i>second revision</i>)
(CED 4)	

Reprography Unit BIS New Delhi India