

AMENDMENT NO. 1 FEBRUARY 1996
TO
IS 5866 : 1979 SPECIFICATION FOR CHROME
LEATHER FOR HIGH ALTITUDE GLOVES

(First Revision)

[Page 6, Table 2, Sl No. (iv), col 2 and 3] — Substitute the following for the existing matter:

(2)	(3)
‘iv) Total ash, percent by mass, Max:	
a) For natural finish leather	3.0*
b) For white pigmented leather	6.0*

*Over the Cr₂O₃ content obtained in Sl No.(i) of the Table.’

(Page 6, clause 3.8, line 2) — Substitute ‘IS 2454 : 1985*’ for ‘IS : 2454 - 1967*’.

(Page 6, foot-note with ‘*’ mark) — Substitute the following for the existing title:

‘*Methods for determination of colour fastness of textile materials to artificial light (xenon lamp) (first revision).’