

AMENDMENT NO. 2 JANUARY 2008
TO
IS 5878 (PART 7) : 1972 CODE OF PRACTICE FOR
CONSTRUCTION OF TUNNELS CONVEYING WATER

PART 7 GROUTING

(Page 3, clause 0.4) — Substitute 'IS 6066' for 'IS 6066 : 1971 Recommendation for pressure grouting of rock foundation in river valley projects'.

(Page 4, clause 0.6) — Delete.

(Page 4, clause 0.7) — Substitute '0.6' for '0.7'.

(Page 4, clause 1) — Insert the following clause after 1 and renumber the subsequent clauses:

2 REFERENCES

2.1 The following standards contain provisions, which through reference in this text constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent additions of the standards indicated in below:

<i>IS No.</i>	<i>Title</i>
269 : 1989	Specification for 33 Grade ordinary Portland cement (<i>fourth revision</i>)
455 : 1989	Specification for Portland slag cement (<i>fourth revision</i>)
1344 : 1981	Specification for calcined clay pozzolana (<i>second revision</i>)
1489 (Part 1) : 1991	Specification for Portland pozzolana cement: Part 1 Flyash based (<i>third revision</i>)
3812 : 1981	Specification for flyash for use as pozzolana and admixture (<i>first revision</i>)

Amend No. 2 to IS 5878 (Part 7) : 1972

<i>IS No.</i>	<i>Title</i>
5878 (Part 6) : 1975	Code of practice for construction of tunnels: Part 6 Steel lining
6066 : 1994	Recommendation for pressure grouting of rock foundation in river valley projects.
8112 : 1989	Specification for 43 grade ordinary Portland cement (<i>first revision</i>)
12269 : 1987	Specification for 53 grade ordinary Portland cement (<i>first revision</i>)

2.2 The reference to Indian Standards, wherever mentioned in this Code, shall be as per clause 2.1.

(Page 12, clause 6.3.5, second sentence) — Substitute ‘7.3.2’ for ‘7.3.1’.

(Page 14, clause 7.3.1) — Substitute the following for the existing:

‘7.3.1 Grouting should be done with cement conforming to IS 269 or IS 8112 or IS 12269 or IS 455 or IS 1489 (Part 1) as specified by the Engineer-in-Charge.’

(Page 14, clause 7.3.4, second sentence) — Substitute the following for the existing:

‘If intake is heavy, the grout may be thickened by incorporation of pozzolana such as flyash conforming to IS 3812 or calcined clay conforming to IS 1344 in the mix or by using inert material like fine sand, rock powder, clay or bentonite.’

(WRD 14)