

AMENDMENT NO. 1 JANUARY 2026
TO
IS 8183 : 2024 BONDED MINERAL WOOL — SPECIFICATION
(Second Revision)

(Page 5, Annex A, clause A-3) — Substitute the following for the existing:

‘A-3 CALCULATION

$$\text{Percentage of the original thickness} = \frac{T_2}{T_1} \times 100$$

where

T_1 = the original thickness, mm; and

T_2 = the thickness after recovery from compression, mm.’

(Page 5, Annex C, clause C-1.1) — Insert the following new clause after C-1.1 and renumber the subsequent clauses:

‘C-2 SAMPLING

C-2.1 Wear clean polyethylene gloves while taking and handling the sample to avoid chloride contamination from perspiration. Do not use gloves made from chloride-containing compounds such as neoprene or saran, or materials with metallic chlorides in their formulations. Prior to use, rinse gloves twice, drain, and air-dry in a clean, halide-free environment. Store clean gloves in a closed container or envelope.

C-2.2 All equipment and working instruments used for this purpose shall be free of soluble chloride, fluoride, silicate, sodium ions and grease. Chloride-free solvents shall be used to clean equipment and working instruments (avoid chlorinated solvents). During the performance of the analytic procedure, extraneous sources of these ions shall be reduced or eliminated.’

(CHD 27)

Price Group 1
Publication, BIS, New Delhi