

**AMENDMENT NO. 1 JULY 1995
TO
IS 8250 : 1988 SPECIFICATION FOR FOUNDRY
PARTING AGENTS**

(First Revision)

(Page 1, clause 5.1) — Substitute the following for the existing clause:

'5.1 Soap Stone Powder — The material shall be offwhite or cream colour having a very smooth and slippery feel. The material shall pass completely through 75 micron IS sieve.

The material shall be predominantly magnesium silicate base soap stone mineral. The chemical composition shall be as agreed to between the buyer and the purchaser and it shall be compatible with the chemical composition of naturally occurring soap stone.'

(MTD 14)

Reprography Unit, BIS, New Delhi, India