

AMENDMENT NO. 1 SEPTEMBER 2001
TO
IS 8329 : 2000 CENTRIFUGALLY CAST (SPUN)
DUCTILE IRON PRESSURE PIPES FOR WATER, GAS
AND SEWAGE — SPECIFICATION

(Third Revision)

(Page 3, clause 4.4) — Delete.

(Page 3, clause 6.1.2) — Substitute the following for the existing clause:

‘6.1.2 For high pressure mains where working pressure is substantial, depending on site condition, suitable flexible joint may be preferred where the joint is restrained against axial movement.’

(Page 4, clause 7.2, lines 14 and 15) — Substitute the following for the existing:

‘all the requirements of clauses 10 and 11.’

(Page 5, clause 10.1.6, Note 2) — Substitute the following for the existing:

‘2 For ductile iron pipes up to DN 1 000, if the microstructure reveals 75 percent ferrite with spheroidal graphite and percentage elongation higher than or equal to 7, it shall be taken as meeting the requirement of this standard when the tensile strength of the specimen is within the specified limit.’

(Page 6, clause 11.1.1, line 1) — Insert ‘minimum’ before ‘Hydrostatic test’.

(Page 6, clause 11.2) — Substitute the following for the existing clause:

‘11.2 Test shall be carried out before the application of surface coating and lining except zinc coating, which may be applied before the hydrostatic test.’

(Page 6, clause 12.2) — Substitute the following for the existing clause:

‘12.2 The critical external diameter of spigot of pipes for push-on flexible joint and mechanical joint for all classes are given in Table 2 for reasons of safety and interchangeability.’

(Pages 8, 9, 10 and 11, Tables 3, 4, 5 and 6) — Delete the existing column 'a'. Title 'b' of the column may be read as 'a'. The letter 'b' in the sketch may be omitted.

(Page 12, clause 15.4) — Substitute the following for the existing:

The tolerance on wall thickness (e) and flange thickness (b) of the pipes shall be as follows:

<i>Sl No.</i>	<i>Dimension</i>	<i>Tolerance, mm</i>
i)	Wall thickness (e) up to 6 mm	-1.3
ii)	Wall thickness (e) above 6 mm	$-(1.3 + 0.001 \text{ DN})^1$
iii)	Flange thickness (b)	$\pm (2 + 0.05b)$

¹The tolerance given is subject to minimum thickness against all classes given in 4.3. No limit for the plus tolerance is specified.'

(Page 12, clause 15.4) — Insert a new clause after 15.4:

'15.4.1 Pipe wall thickness compliance shall be demonstrated by the manufacturer, he may use combination of various means such as:

- Direct wall thickness measuring or gauging by suitable requirements such as mechanical or ultrasonic equipment.
- The frequency of testing is related to the system of production and quality control used by manufacturer.

(Page 13, clause 16.1) — Substitute the following for the existing:

'16.1 Unless otherwise agreed between the manufacturer and the purchaser, all pipes shall be delivered with an external bituminous coating in accordance with provisions of Annex C.'

(Page 13, clause 16.2, line 8) — Delete the sentence 'Bituminous paint : as included in Annex C'.

(Page 17, Table 15, col 4) — Substitute the following for the existing values:

'0.8, 1.0, 1.2 and 1.5' respectively.

(Page 19, Annex E) — Substitute the following for the existing:

ANNEX E
(Table 1)

**HYDROSTATIC SITE TEST PRESSURES AND
HYDRAULIC WORKING PRESSURE**

DN (mm)	Allowable Operating Pressure (excluding surge) AOP				Allowable Maximum Operating Pressure (including surge) MOP				Allowable Site Test Pressure (STP)			
	K7	K8	K9	K10	K7	K8	K9	K10	K7	K8	K9	K10
MPa					MPa				MPa			
80	0.8	6.4	6.4	6.4	1.25	7.7	7.7	7.7	1.75	9.6	9.6	9.6
100	0.8	6.4	6.4	6.4	1.25	7.7	7.7	7.7	1.75	9.6	9.6	9.6
125	0.8	6.4	6.4	6.4	1.25	7.7	7.7	7.7	1.75	9.6	9.6	9.6
150	0.8	6.4	6.4	6.4	1.25	7.7	7.7	7.7	1.75	9.6	9.6	9.6
200	0.8	1.0	6.2	6.4	1.25	1.5	7.4	7.7	1.75	2.0	7.9	9.6
250	0.8	1.0	5.4	6.1	1.25	1.5	6.5	7.3	1.75	2.0	7.0	7.8
300	0.8	1.0	4.9	5.6	1.25	1.5	5.9	6.7	1.75	2.0	6.4	7.2
350	0.8	1.0	4.5	5.1	1.25	1.5	5.4	6.1	1.75	2.0	5.9	6.6
400	0.8	1.0	4.2	4.8	1.25	1.5	5.1	5.8	1.75	2.0	5.6	6.3
450	0.8	1.0	4.0	4.5	1.25	1.5	4.8	5.4	1.75	2.0	5.3	5.9
500	0.8	1.0	3.8	4.4	1.25	1.5	4.6	5.3	1.75	2.0	5.1	5.8
600	0.8	1.0	3.6	4.1	1.25	1.5	4.3	4.9	1.75	2.0	4.8	5.4
700	0.8	1.0	3.4	3.8	1.25	1.5	4.1	4.6	1.75	2.0	4.6	5.1
750	0.8	1.0	3.3	3.7	1.25	1.5	3.9	4.4	1.75	2.0	4.4	4.9
800	1.0	1.0	3.2	3.6	1.5	1.5	3.8	4.3	2.0	2.0	4.3	4.8
900	1.0	1.0	3.1	3.5	1.5	1.5	3.7	4.2	2.0	2.0	4.2	4.7
1 000	1.0	1.0	3.0	3.4	1.5	1.5	3.6	4.1	2.0	2.0	4.1	4.6
1 100	2.9	2.9	2.9	3.2	3.5	3.5	3.5	3.8	4.0	4.0	4.0	4.3
1 200	2.8	2.8	2.8	3.2	3.4	3.4	3.4	3.8	3.9	3.9	3.9	4.3
1 400	2.8	2.8	2.8	3.1	3.3	3.3	3.3	3.7	3.8	3.8	3.8	4.2
1 600	2.7	2.7	2.7	3.0	3.2	3.2	3.2	3.6	3.7	3.7	3.7	4.1
1 800	2.6	2.6	2.6	3.0	3.1	3.1	3.1	3.6	3.6	3.6	3.6	4.1
2 000	2.6	2.6	2.6	2.9	3.1	3.1	3.1	3.5	3.6	3.6	3.6	4.0

(MTD 6)