

AMENDMENT NO. 3 FEBRUARY 2014
TO
IS 8329 : 2000 CENTRIFUGALLY CAST (SPUN)
DUCTILE IRON PRESSURE PIPES FOR WATER,
GAS AND SEWAGE — SPECIFICATION

(Third Revision)

(Page 3, clause 6.2.2) — Insert the following sentence at the end:

‘Welding on flanges will not be allowed on the screwed flange pipe.’

[Page 5, clause 10.1.6, Notes 1, 2 and 3 (see also Amendment No. 1)] — Substitute the following for existing:

‘NOTE 1 The 0.2% proof stress may be measured. It shall be not less than 270 MPa when minimum elongation after fracture $A \geq 12\%$ for DN80 to DN1000 or $A \geq 10\%$ for DN > 1000 and 300 MPa in other case. For centrifugally cast pipes for DN 80 to DN 1000 and having a design minimum wall thickness of 10 mm or greater, the minimum elongation after fracture shall be 7 percent.

(Page 5, clause 10.1.6, Note 4) — Substitute ‘Note 2’ for ‘Note 4’.

(Page 6, clause 11.2) — Insert a new clause as follows:

‘11.2.1 In case of flange pipe, the hydrostatic testing shall be done again after flanging at specified pressure on lined and coated pipes.’

(Page 8, Table 3, Note 2) — Delete.

(Page 8, Table 3, Note 3) — Substitute the following for the existing Note:

‘2 Dimension ‘s’ is for guidance only’

(Page 8, Table 3, Note 4) — Substitute the existing footnote:

‘3 Flanged dimension may be allowed as per customer specification and it shall not be less than PN 10 thickness.’

Amendment No. 3 to IS 8329 : 2000

(Page 9, Table 4, Note 2) — Delete.

(Page 9, Table 4, Note 3) — Substitute the following for the existing:

‘2 Dimension ‘s’ is for guidance only’.

(Page 9, Table 4, Note 4) — Substitute the following for the existing footnote:

‘3 Flanged dimension may be allowed as per customer specification and it shall not be less than PN 10 thickness.’

(Page 10, Table 5, Note 2) — Delete.

(Page 10, Table 5, Note 3) — Substitute the following for the existing Note:

‘2 Dimension ‘s’ is for guidance only’

(Page 10, Table 5, Note 4) — Substitute the existing footnote:

‘3 Flanged dimension may be allowed as per customer specification and it shall not be less than PN 10 thickness.’

(Page 11, Table 6, Note 2) — Delete

(Page 11, Table 6, Note 3) — Substitute the following for the existing Note:

‘2 Dimension ‘s’ is for guidance only.’

(Page 11, Table 6, Note 4) — Substitute the existing footnote:

‘3 Flanged dimension may be allowed as per customer specification and it shall not be less than PN 10 thickness.’