

AMENDMENT NO. 5 JANUARY 2019
TO
IS 8329 : 2000 CENTRIFUGALLY CAST (SPUN) DUCTILE
IRON PRESSURE PIPES FOR WATER, GAS AND
SEWAGE — SPECIFICATION

(Third Revision)

(Page 6, clause 11.1.1) — Substitute the following for the existing clause:

‘11.1.1 The minimum hydrostatic test pressure at works ‘ p ’, expressed in MPa, is to be calculated as function of the coefficient K (see 4.3) by using the following formulae :’

a) $DN\ 80\ to\ 300p = 0.05 (K + 1)^2$

b) $DN\ 350\ to\ 600p = 0.05 (K)^2$

c) $DN\ 700\ to\ 1\ 000p = 0.05 (K - 1)^2$

d) $DN\ 1100\ to\ 2\ 000p = 0.05 (K - 2)^2$

[Page 16, clause B-1.1 a)] — Substitute the following for the existing:

‘a) Portland cement (as per IS 8112 or IS 455) mortar lining perform rather well in line with the life of the pipe in soft water with moderate amount of aggressive CO_2 and when pH is within 6.0 to 9.0.’