

AMENDMENT NO. 1 NOVEMBER 2020

TO

**IS 8419 (PART 1) : 1977 REQUIREMENTS FOR
FILTRATION EQUIPMENT**

PART 1 FILTRATION MEDIA — SAND AND GRAVEL

(Page 4, clause 2.1, line 2) — Substitute ‘IS 2720 (Part 4) : 1985*’ for ‘IS : 2720 (Part IV)-1975*’

(Page 4, clause 3.1.1) — Substitute the following for the existing clause:

‘3.1.1 Filter sand shall consist of hard and durable grains of silica with a specific gravity of not less than 2.5 when tested in accordance with IS 2386 (Part 3) : 1963‡. All grains of sand shall preferably be water worn. The minimum silica content in sand as determined by the method given in IS 2000 (Part 2) : 1985† shall be 90 percent.’

(Page 4, footnotes) — Substitute the following for the existing:

*Methods of test for soils: Part 4 Grain size analysis (*second revision*).

‡ Methods of test for aggregates for concrete: Part 3 Specific gravity, density, voids, absorption and bulking.

† Methods of chemical analysis of bauxite: Part 2 Determination of silica (*first revision*).’

(Page 5, clause 4.1.1, sentence 1) — Substitute the following for the existing:

‘4.1.1 Filter gravel shall consist of hard, preferably rounded stones with a specific gravity of not less than 2.5 when tested in accordance with IS 2386 (Part 3) : 1963*. Filter gravel shall be free from clay, sand, loam and organic impurities of any kind.’

113.199.238.108
Amendment No. 1 to IS 8419 (Part 1) : 1977

(Page 5) — Insert the following footnote:

‘* Methods of test for aggregates for concrete: Part 3 Specific gravity, density, voids, absorption and bulking.’

(Page 6, clause 4.2.4) — Add the following new clauses at the end:

‘5 SUPPLIER’S/MANUFACTURER’S CERTIFICATE

The supplier/manufacturer shall furnish a certificate to the purchaser or his representative within ten days of dispatch of the filter sand/gravel stating that the material conforms to all the requirements of this standard.

6 DELIVERY

Supplies of filter sand/gravel may be made in bulk in suitable quantities mutually agreed upon between the purchaser and the supplier. Where so required by the purchaser, the filter sand/gravel may be supplied in bags (jute, jute-laminated, polyethylene lined or as may be mutually agreed between the purchaser and the supplier) bearing the net quantity (may be 25 kg, 50 kg or as agreed to between the purchaser and the supplier).

7 MARKING

7.1 Each consignment/bag of filter sand/gravel shall be legibly and indelibly marked with the following information:

- a) Manufacturers name and his registered trademark, if any;
- b) Net quantity, in kg;
- c) Address of the manufacturer;
- d) Month and year of consignment/packing; and
- e) Type of filtration media, such as ‘Filter Sand’ or ‘Filter Gravel’.

7.2 Similar information shall be provided in the delivery advices accompanying the shipment of filter sand/gravel in bulk (*see 6.3*).

7.3 BIS Certification Marking

The filter sand/gravel conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act*, 2016 and the Rules and Regulations framed thereunder, and the consignments of filter sand/gravel may be marked with the Standard Mark.

Amendment No. 1 to IS 8419 (Part 1) : 1977

(Page 6, clause **B-1.1**, line 2) — Substitute ‘ 105 ± 2 °C’ for ‘103 °C’.

(Page 7, clause **C-1.1**, line 2) — Substitute ‘ 105 ± 2 °C’ for ‘103 °C’.

(Page 7, clause **C-1.1**, line 2) — Substitute ‘ 550 ± 10 °C’ for ‘550 °C’.