

AMENDMENT NO. 1 OCTOBER 2009
TO
IS 8455 : 1977 RECOMMENDED PROCEDURE FOR WELDING OF POLYETHYLENE

(Page 8, clause 3.6.1, last line) — Substitute '20°C' for '20°'.

(Page 9, clause 3.9, line 2) — Substitute '60 % of the strength of parent' for '0.6 times the strength of the parent'.

(Page 9, clause 4.2, line 4) — Substitute 'Residue' for 'Residues of PE'.

(Page 12, clause 4.7, heading) — Substitute 'Weld Finish' for 'Weld Finishing'.

(Page 13, clause 5.8, line 2) — Substitute '60 % of the strength of parent material' for '60 to 80' percent of the strength of parent metal'.

(Page 14, clause 6.8) — Substitute the following for the existing clause:

'6.8 Quality of weld — The quality of the finished joint depends on the following factors:

- a) Taper angle wherever applicable,
- b) Speed of rotator and movement of the clamps,
- c) Cleanness of the connecting surface, and
- d) Skill of the welder.

6.8.1 In friction welding butt joints of strength equal to that of the parent material is achieved.'