

AMENDMENT NO. 1
TO
IS : 8467 - 1977 SPECIFICATION FOR
STEEL CARD-INDEX CABINETS

Alteration

(*Pages 8 and 9, clauses 7.1, 7.2 and 7.2.1*) — Substitute the following for the existing clauses:

“7.1 All dents, burrs and sharp edges shall be removed from the various components. The components shall be individually pickled, scrubbed and rinsed to remove grease, rust, scale or any other foreign element.

7.2 Immediately after pickling, all the mild steel parts shall be given phosphating treatment conforming to Class C of IS : 3618-1966*. The process for application of phosphate coating shall be in accordance with IS : 6005-1970 ‘ Code of practice for phosphating of iron and steel’ .

NOTE — Putty shall be applied to all the surfaces requiring filling and shall conform to IS : 426-1961§. Aluminium primer shall conform to IS : 2931-1964||.

7.2.1 Coat/Coats of enamel paint shall then be applied as follows:

- a) Finish coat with enamels conforming to IS : 151-1950* IS : 2932-1974†, or IS : 2933-1975‡; and
- b) In the case of stoving enamel the components shall thereafter be baked at a specified temperature in an oven heated uniformly. The finish shall be smooth and uniform with a hard and tough film of enamel strongly adhering to the surface. The finish shall be free from all visible defects and shall not chip when tapped lightly with a dull pointed instrument.”

Addenda

(*Page 9, clause 7.3*) — Add the following new clauses after 7.3 and renumber the subsequent clauses accordingly:

‘8. PERFORMANCE REQUIREMENTS OF FINISH

8.1 Scratch Hardness Test — A sample of mild steel plate 150 × 50 mm in size and thickness 0.315 mm finished as described in 7 shall be subjected to scratch hardness test in accordance with 15.1 of IS : 101-1964¶. A scratch, showing the bare metal shall not be produced on the test sample.