

**AMENDMENT NO. 1 NOVEMBER 2011
TO
IS 4020 (PART 7) : 1998 DOOR SHUTTERS —
METHODS OF TESTS**

PART 7 EDGE LOADING TEST

(Third Revision)

(Page 7, clause 2) — Substitute the following for the existing:

‘The door shutter shall be hung vertically, bearing or with 12 mm dia pivot supported at the top and bottom or hinged on one longitudinal edge. The test set up shall be sufficiently rigid to withstand the test load without deflecting to an extent likely to impair jointing or to impose bending stresses on the test specimen. If installation conditions are known, the specimen shall wherever practical, be installed to simulate these. The door shall be opened at an angle of 45° or 90° and measurements taken at the lower corner of the door shutter, to the nearest 0.1 mm. The load shall be applied on the top of the other longitudinal edge parallel to the plane of the door shutter at a distance of 50 mm from the edge. The loading shall be done in steps of not more than 200 N (20 kgf) at a time until a load of 1 000 N (100 kgf) is reached and kept constant for a period of 15 min. The deflection at the loaded edge, at the end of 15 min and after 3 min after removal of the load, measured to an accuracy of 0.1 mm, shall be recorded.’