

AMENDMENT NO. 2 MAY 2009
TO
IS 4021 : 1995 TIMBER DOOR, WINDOW AND
VENTILATOR FRAMES — SPECIFICATION

(Third Revision)

(Second cover page, Foreword, third para) — Insert ‘as given in Annex B’ between ‘list’ and ‘has’ in the ninth line.

(Page 2, clause 4.1.3, eighth line) — Substitute ‘IS 401 : 2001’ for ‘IS 401 : 1982’.

(Page 6, clause 5.3, sixth line) — Substitute ‘IS 848 : 2006’ for ‘IS 848 : 1974’.

(Page 8, clause 7) — Substitute ‘**METALLIC FASTENERS/HOLDFASTS**’ for ‘**HOLDFASTS**’ in the title and wherever appearing in the clause.

(Page 8, clause 8.3) — Substitute ‘IS 3536 : 1999’ for ‘IS 3536 : 1966’.

[Page 9, clause 10 (see also Amendment No. 1)] — Insert ‘**ADDITIONAL**’ before the existing title.

(Page 10, Annex A) — Substitute the following for the existing, as appropriate:

‘IS 401 : 2001	Code of practice for preservation of timber (<i>fourth revision</i>)
IS 848 : 2006	Synthetic resin adhesives for plywood (phenolic and aminoplastic) — Specification (<i>second revision</i>)
IS 3536:1999	Ready mixed paint, brushing, wood primer — Specification (<i>first revision</i>)’

(Page 11, Annex B) — Substitute the following matter appearing on page 2 for the existing:

ANNEX B
(Foreword, and Clause 4.1.1)

**LIST OF SPECIES OF TIMBER BEING IMPORTED FOR FRAMES OF DOORS AND
WINDOWS CONSIDERED SUITABLE FROM THE FOREIGN LITERATURE AVAILABLE**

Sl No.	Trade Name	Botanical Name	Country from Where Imported
(1)	(2)	(3)	(4)
i)	Abura	<i>Mitragyna stipulosa</i>	Africa (A)
ii)	Afrormosia*	<i>Afrormosia angolensis</i>	(A)
iii)	Alan Batu†	<i>Shorea albida</i>	Malaysia (M)
iv)	Amoora†	<i>Ammore cucullata</i>	Papua New Guinea (PNG)
v)	Bitangor	<i>Calophyllum</i> spp.	(M)
vi)	Dark Red Meranti†	<i>Shorea</i> spp.	(M)
vii)	Durian	<i>Coelostegia</i> spp. <i>Duria</i> spp. and <i>Neesia</i> spp.	(M)
viii)	Iroko*	<i>Chlorophora excelsa</i>	(A)
ix)	Keuring	<i>Dipterocarpus</i> spp.	(M)
x)	Kwila†	<i>Instia bijuga</i>	(PNG)
xi)	Light Red Meranti†	<i>Shorea</i> spp.	(M)
xii)	Merawan†	<i>Hopea</i> spp.	(M)
xiii)	Merbau†	<i>Intsia palembanica</i>	(M)
xiv)	Nyato†	<i>Ganua</i> spp., <i>Palaquium</i> spp. and <i>Payuena</i> spp.	(M)
xv)	Nyato kuring†	<i>Planchonella</i> spp. and <i>Pouteria</i> spp.	(M)
xvi)	Sapela†	<i>Entandophragma cylindrium</i>	(A)
xvii)	Terminalia red brown group†	<i>Terminalia</i> spp.	(PNG)
xviii)	Utile†	<i>Entandophragma utile</i>	(A)
xix)	Vitex†	<i>Vitex cofassus</i>	(PNG)

NOTE — Above imported species shall be used for frames only after proper treatment as prescribed in IS 401 : 2001 and concerned clauses of this standard, as suitable and sufficient information regarding their durability is not available and whatever is available may not fully hold good in Indian conditions. However, heartwood of species marked ‘*’ does not require treatment as the same is reported to be very durable. Further, where sufficient retention/absorption/penetration of preservative is not obtained as per IS 401 : 2001 due to poor treatability character of the species, the frame shall be treated with PCP solvent system after construction to ensure minimum penetration of preservative to the depth of 2 mm in the finished product by soaking in 5 % PCP solution for 24 h or pressure treatment. Such species which are refractory to treatment are marked ‘†’.

(CED 11)

Reprography Unit, BIS, New Delhi, India