

AMENDMENT NO. 2 DECEMBER 1978

TO IS : 4072-1975 SPECIFICATION FOR STEEL FOR SPRING WASHERS

(*First Revision*)

Alteration

(Page 4, Table 1) — Substitute the following for the existing table:

TABLE 1 CHEMICAL COMPOSITION

(*Clauses 2.1, 5.1 and 5.2*)

GRADE	DESIGNATION	CONSTITUENT, PERCENT						
		Carbon	Silicon	Manganese	Sulphur, <i>Max</i>	Phosphorus, <i>Max</i>	Chromium	Vanadium
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)
1	55C6	0.50 to 0.60	0.10 to 0.35	0.50 to 0.65	0.050	0.050	—	—
2	65C6	0.60 to 0.70	0.10 to 0.35	0.50 to 0.80	0.050	0.050	—	—
3	70C6	0.65 to 0.75	0.10 to 0.35	0.50 to 0.80	0.050	0.050	—	—
4	80C6	0.75 to 0.85	0.10 to 0.35	0.50 to 0.80	0.050	0.050	—	—
5	38Si7	0.35 to 0.42	1.50 to 1.90	0.60 to 0.80	0.040	0.040	—	—
6	50Si7	0.45 to 0.55	1.50 to 2.00	0.50 to 0.80	0.050	0.050	—	—
7	55Si7	0.50 to 0.60	1.50 to 2.00	0.70 to 1.00	0.050	0.050	—	—
8	60Si7	0.55 to 0.65	1.50 to 2.00	0.70 to 1.00	0.050	0.050	—	—
9	50CrV4	0.47 to 0.55	0.15 to 0.35	0.80 to 1.10	0.035	0.035	0.90 to 1.20	0.07 to 0.12

(SMDC 5)