

AMENDMENT NO. 1    JANUARY 1987  
TO  
IS:4098-1983 SPECIFICATION FOR LIME-POZZOLANA MIXTURE  
(First Revision)

(Page 4, clause 3.1, first sentence) -  
Substitute the following for the existing matter:

'Lime-pozzolana mixture shall be manufactured either by intergrinding Class C hydrated lime (see IS:712-1984<sup>5</sup>) and pozzolam, such as calcined clay (see IS:1344-1981<sup>II</sup>) or fly ash (see IS:3812-1981<sup>5</sup>) or rice husk ash in suitable proportions in a ball or tube mill, or by blending the ingredients in the form of powder to comply with the requirements of this specification.'

(Page 4, foot-note with '5' mark) - Substitute 'third revision' for 'second revision'.

(BDC 4)