

AMENDMENT NO. 2 MARCH 2002
TO
IS 3302: 1986 SPECIFICATION FOR BACKING SHEET
FOR STENCIL
(First Revision)

(Page 3, clause 2.1) — Substitute the following for the existing:

'2.1 For the purpose of this standard, the definitions given in IS 4661 : 1999† shall apply.'

(Page 3, footnote with '†' mark) — Substitute the following for the existing:

'Glossary of terms used in paper trade and industries (second revision).'

[Page 4, clause 3.1 (see also Amendment No. 1)] — Insert the following new clause after 3.1 and renumber the subsequent clauses:

'3.2 Grammage — The nominal grammage of backing sheet shall be 75 g/m² or higher as agreed to between the seller and the buyer. A tolerance of the ±5 percent for individual test results and ±2.5 percent for average of ten test results shall be allowed on nominal grammage when tested in accordance with 6 of IS 1060 (Part 1) : 1966.'

(Page 4, Table 1) — Substitute the following for the existing:

Amend No. 2 to IS 3302 : 1986

Table 1 Requirements for Backing Sheet for Stencil
(*Clause 3.1*)

Sl No.	Characteristic	Requirement	Method of Test Ref to CI No. in IS 1060 (Part 1) : 1966]*
(1)	(2)	(3)	(4)
i)	Burst index, kPa.m ² /g, <i>Min</i>	1.0	12.5
ii)	Tensile index, N.m/g, <i>Min</i>		
	a) Machine direction	25.0	12.3
	b) Cross direction	17.0	
iii)	Tear index, mN.m ² /g, <i>Min</i>	4.0	12.7
iv)	One minute Cobb value, g/m ² , <i>Max</i>	25	13.2.2

Tensile index = Breaking length, m $\times$ 0.009 8;

Tear index = Tear factor $\times$ 0.098.

*Methods of sampling and test for paper and allied products : Part 1 (revised).

[*Page 4, clause 4.2(b)*] — Substitute 'Grammage' for 'Substance'

(CHD 15)

Reprography Unit, BIS, New Delhi, India