

AMENDMENT NO. 2 NOVEMBER 1980

TO

IS : 3326 - 1978 SPECIFICATION FOR COTTON STOCKINETTE

(*First Revision*)

[This amendment is being issued to incorporate the requirement of number of wales per decimetre as an alternate to the total number of wales of stockinette.]

Alteration

[*Page 4, Table 1, Sl No. (i) (see also Amendment No. 1)* — Substitute the following for the existing matter under respective columns:

(1)	(2)	(3)	(4)
i)	Total wales	360 ± 20	A-1.1
	or		
	Wales/dm	65 ± 5	A-1.2'

Addendum

(*Page 6, clause A-1.1*) —Add the following new clause after **A-1.1**:
'**A-1.2** Take a piece constituting the test sample. Lay it flat on a horizontal surface (*see Note under A-1.1*). Remove all creases and wrinkles without distorting the piece. Count with the help of a pick glass or magnifying glass, the number of wales per decimetre of the fabric at six different, viz at the two extreme and middle portions on the front as well as at the back. Calculate the average of the six readings to determine the number of wales per decimetre.'