

**AMENDMENT NO. 2 JUNE 2005
TO
IS 3348 : 1965 SPECIFICATION FOR
FIBRE INSULATION BOARDS**

(Page 4, clause 3) — Substitute the following for the existing

3 DIMENSIONS AND TOLERANCES

3.1 The dimensions of fibre insulation boards shall be as follows

Length in mm 3 600, 3 000, 2 700, 2 400, 2 100, 1 800, 1 500, 1 200,
1 000, 900, 600, 450 and 300

Width in mm 1 800, 1 500, 1 200, 1 000, 900, 600, 450 and 300

3.2 Thickness

The thickness of fibre insulation boards shall be 9 mm, 12 mm, 18 mm and 25 mm

NOTE — Any other dimension (length, width and thickness) as agreed to between the manufacturer and the purchaser may also be used

3.3 Tolerances

The tolerances on the nominal sizes of finished boards shall be as follows

<i>Dimensions</i>	<i>Tolerances</i>
Length	+ 6 mm - 0 mm
Width	+ 3 mm - 0 mm
Thickness	± 5 percent
Edge straightness	2 mm per 1 000 mm or 0.2 percent
Squareness	2 mm per 1 000 mm or 0.2 percent

(CED 20)

Reprography Unit, BIS, New Delhi, India