

**AMENDMENT NO. 1 FEBRUARY 2000
TO
IS 3447 : 1993 SHELLAC JOINTING COMPOUND —
SPECIFICATION**

(First Revision)

(*Page 1, clause 2*) — Insert 'IS 1839 : 1961 Toluene, reagent grade' and 'IS 2796 : 1995 Motor gasoline — Specification (*second revision*)' after 'IS 1260 (Part 1) : 1973'.

(*Page 1, clause 4.1*) — Substitute the following for the existing:
'The material shall be a viscous homogeneous solution of shellac [*see* IS 16 (Part 1) : 1991] in denatured spirit (*see* IS 324) together with some additives and shall be free from dust, grit and other visible impurities.'

(*Page 1, clause 4.3*) — Substitute the following for the existing:
'The total solids in the material shall be between 50 to 58 percent when determined by the method prescribed in Annex A.'

(*Page 1, clause 4.5, line 2*) — Substitute '52' for '50'.

(*Page 1*) — Insert the following new clause after 4.5:

'4.6 Resistance to Motor Gasoline-Toluene Mixture

The film of the material shall not become soft or develop any cracks when tested as prescribed in Annex D.'

(*Page 2, clause 6.1, line 2*) — Substitute 'Annex E' for 'Annex D'.

(*Page 3*) — Insert the following new 'Annex D' after 'Annex C' and renumber the subsequent Annex:

Amend No. 1 to IS 3447 : 1993

**‘ANNEX D
(Clause 4.6)**

**DETERMINATION OF RESISTANCE TO MOTOR GASOLINE AND
TOLUENE MIXTURE**

D-1 PRINCIPLE

D-1.1 The resistance to motor gasoline-toluene mixture is determined by dipping the dried film of the material, applied on the aluminium panel, in motor gasoline-toluene mixture for 24 h and examining the film for any softening or cracks.

D-2 APPARATUS

D-2.1 Aluminium Panel

D-3 REAGENTS

D-3.1 Motor Gasoline (*see* IS 2796) and Toluene (*see* IS 1839) Mixture — 3:1 (v/v).

D-3.2 Trichloroethylene — (*see* IS 245).

D-4 PROCEDURE

D-4.1 Clean the aluminium panel with trichloroethylene by rubbing with a clean dry cloth and allow it to dry. Apply a uniform coating of the material with a brush on the panel and allow it to dry in air in a horizontal position for 48 h at room temperature. Immerse this panel in a stoppered container containing motor gasoline-toluene mixture and close it with the stopper. Remove the panel after 24 h and examine the film immediately for any softening or cracks.

D-4.2 Allow this panel to dry at room temperature for 24 h and examine again for any cracks developed on the film.’

(PCD 12)