

AMENDMENT NO. 3 SEPTEMBER 2005
TO
IS 3478 : 1966 SPECIFICATION FOR
HIGH DENSITY WOOD PARTICLE BOARDS

(*Page 5, clause 6*) — Substitute the following for the existing:

6 DIMENSIONS AND TOLERANCES

6.1 The dimensions of high density particle boards shall be as follows:

Length in mm : 2 400, 2 100, 1 800, 1 500, 1 200, 1 000, 900, 600
and 450

Width in mm : 1 500, 1 200, 1 000, 900, 600, and 450

NOTE — Any other dimension as agreed to between the manufacturer and the purchaser may also be used.

6.2 Thickness

The thickness of high density particle boards shall be 4 mm, 6 mm, 9 mm, 12 mm, 15 mm, 20 mm, 25 mm, 30 mm, 35 mm, 40 mm and 50 mm.

6.3 Tolerances

The tolerances on the nominal sizes of finished boards shall be as follows:

<i>Dimensions</i>	<i>Tolerances</i>
Length	+ 6 mm - 0 mm
Width	+ 3 mm - 0 mm
Thickness:	
i) Less than 6 mm	±10 percent
ii) 6 mm and above	±5 percent
Edge straightness	2 mm per 1 000 mm or 0.2 percent
Squareness	2 mm per 1 000 mm or 0.2 percent

(Page 6, clause **8.2.5**) — Substitute ‘*Modulus of Elasticity and Modulus of Rupture*’ for the existing title and ‘modulus of elasticity and modulus of rupture’ for ‘modulus of rupture’ in the last line.

(Page 7, Table 1) — Substitute the following for the existing table:

Table 1 Physical Requirements for High Density Wood Particle Boards
(Clauses 7.2 and 9.2)

Type	Grade	Density	Moisture Content	Modulus of Rupture		Modulus of Elasticity		Minimum Tensile Strength	Water Absorption After 24 h Maximum Immersion	Resistance to Boiling Water After 3 h Immersion
(1)	(2)	(3)	(4)	(5)		(6)		(7)	(8)	(9)
		g/cm ²	percent	N/mm ²		N/mm ²		N/mm ²	percent	
Type 1	Grade A	1.2	3 to 7	Avj	Min	Avj	Min	35.0	10	Shall not show any sign of delamination
	Grade B	0.9 Min	5 to 16	45.0	38.0	4 500	4 050	30.0	25	
Type 2	Grade A	1.2	5 to 10	30.0	25.0	3 000	2 700	22.5	15	Not specified
	Grade B	0.9 Min	5 to 16	25.0	21.0	2 500	2 250	20.0	25	
Test According to		IS 2380 (Part 3) : 1977*	IS 2380 (Part 3) : 1977*	IS 2380 (Part 4) : 1977*		IS 2380 (Part 4) : 1977*		IS 2380 (Part 5) : 1977*	IS 2380 (Part 16) : 1977*	9.3
Maximum Permissible Variation in Individual Specimens From the Mean			Max ±10 percent	Max ± 2 percent		—		—	—	—
*Method of test for wood particle boards and boards from other lignocellulosic materials.										