

AMENDMENT NO. 1 JUNE 2005
TO
IS 3513 (PART 2) : 1989 SPECIFICATION FOR
RESIN TREATED COMPRESSED WOOD LAMINATES
(COMPREGS)
PART 2 FOR CHEMICAL PURPOSES
(First Revision)

(*Pages 2 and 3, clauses 7.1 and 7.1.1*) — Substitute the following for the existing:

‘7.1 Boards

The dimensions of resin treated compressed wood laminate boards shall be as follows:

Length in mm : 2 400, 2 100, 1 800, 1 500, 1 200, 900 and 600

Width in mm : 1 200, 900, 600, 300 and 150

NOTE — Any other dimension as agreed to between the manufacturer and the purchaser may also be used.’

(*Page 3, clause 7.1.2*) — Renumber the clause and substitute the following for the existing:

‘7.1.1 Thickness

Unless otherwise specified the thickness of resin treated compressed wood laminate boards shall be 3 mm, 4 mm, 5 mm, 6 mm, 8 mm, 12 mm, 16 mm, 20 mm, 25 mm, 32 mm, 40 mm, 50 mm, 60 mm and 70 mm.’

(*Page 3, clause 7.1.3*) — Renumber the clause and substitute the following for the existing:

7.1.2 Tolerances

The tolerance on the nominal sizes of finished boards shall be as follows:

Amend No. 1 to IS 3513 (Part 2) : 1989

<i>Dimensions</i>	<i>Tolarance</i>
Length	+6 mm -0 mm
Width	+3 mm -0 mm
Thickness:	
i) Less than 6 mm	±10 percent
ii) 6 mm and above	±5 percent
Edge straightness	2 mm per 1 000 mm or 0.2 percent
Squareness	2 mm per 1 000 mm or 0.2 percent

(CED 20)