

AMENDMENT NO. 1 SEPTEMBER 1977
TO
IS:7370-1974 SPECIFICATION FOR
RAZORS, SAFETY
Alterations

(Page 6, clause 5.2) • Substitute the following for the existing clause:

5.1 The components of safety razors made of non-ferrous metal, except aluminium, shall be nickel-plated having a thickness of of nickel-plating of 20 microns or more. For other requirements the nickel-plating shall conform to Service Grade Ho. 3 of IS2^827-1968*. The aluminium components shall be anodized in accordance with Grade AC 5 of IS:1868-1968+.

(Page 7, clause 7.t) - Substitute the following for the existing clause:

'7.1 Parallelism of Blade and Razor Guard ~ Using a new blade conforming to IS:7371-1975* the parallelism of the razor shall be checked by (a) mechanical method as described in 7.1.1 or (b) optical method as described in 7.1.2. The difference between the minimum and maximum readings shall not exceed 0.15 mm to comply with 4.7. The straightness of the blade shall first be checked and any deviation, if found, shall be taken into account. The test shall be conducted on both shaving sides of the razor.

7.1.1 The following procedure shall be adopted for mechanical methods

- a) Inserting the blade in the razor*
- b) Trueing the razor up in either V-blocks or a fixture by levelling the razor by-dial indicator* gauging the blade on top of both ends of the cutting edge,
- c) Relocating the dial indicator anvil to obtain a reading on the top of the guard, and
- d) Moving the dial indicator gauge across the top edge of the guard*

7.1.2 The following procedure- shall be adopted for optical method:

- a) Inserting the blade in the razor,
- b) Trueing the blade at both ends under the optical microscope, and
- c) Comparing the edge of the blade with that of the razor guard.'

(CPDC 6)